

DYNAMID DYN-N66G15L NC

Polyamide 66
Dynamic Polymer Solutions

Technical Data

Product Description			
Polyamide 66, 15% glass fiber reinforced & lubricated natural			
General			
Material Status	• Commercial: Active		
Literature ¹	• Technical Datasheet (English)		
Availability	• North America		
Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight		
Additive	• Lubricant		
Features	• Good Stiffness	• Good Strength	• Lubricated
Appearance	• Natural Color		
Processing Method	• Injection Molding		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity			
--	1.24	1.24 g/cm ³	ASTM D792
73°F (23°C)	1.24 g/cm ³	1.24 g/cm ³	ISO 1183
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus			
-- ³	791000 psi	5450 MPa	ASTM D638
--	790000 psi	5450 MPa	ISO 527-1/10
Tensile Strength			
Yield ⁴	15800 psi	109 MPa	ASTM D638
Yield	15700 psi	108 MPa	ISO 527-2/50
Tensile Elongation			
Break ⁴	5.0 %	5.0 %	ASTM D638
Break	3.0 %	3.0 %	ISO 527-2/50
Flexural Modulus ⁵			
--	700000 psi	4830 MPa	ASTM D790
--	754000 psi	5200 MPa	ISO 178
Flexural Strength ⁵			
--	25000 psi	172 MPa	ASTM D790
--	26100 psi	180 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	1.6 ft·lb/in ²	3.3 kJ/m ²	ISO 179
Notched Izod Impact			
73°F (23°C)	1.2 ft·lb/in	64 J/m	ASTM D256
73°F (23°C)	3.4 ft·lb/in ²	7.2 kJ/m ²	ISO 180



DYNAMID DYN-N66G15L NC

Polyamide 66

Dynamic Polymer Solutions

PROSPECTOR®

www.ulprospector.com

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 psi (0.45 MPa), Unannealed	480 °F	249 °C	ASTM D648
66 psi (0.45 MPa), Unannealed	482 °F	250 °C	ISO 75-2/B
264 psi (1.8 MPa), Unannealed	466 °F	241 °C	ASTM D648
264 psi (1.8 MPa), Unannealed	464 °F	240 °C	ISO 75-2/A
Peak Melting Temperature	504 °F	262 °C	ASTM D3418 ISO 3146

Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	212 to 248 °F	100 to 120 °C
Drying Time	3.0 to 5.0 hr	3.0 to 5.0 hr
Suggested Max Moisture	< 0.15 %	< 0.15 %
Processing (Melt) Temp	545 to 590 °F	285 to 310 °C
Mold Temperature	149 to 194 °F	65 to 90 °C
Injection Rate	Fast	Fast
Back Pressure	100 to 150 psi	0.689 to 1.03 MPa

Notes

- ¹ These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.
- ² Typical properties: these are not to be construed as specifications.
- ³ 0.39 in/min (10 mm/min)
- ⁴ 2.0 in/min (50 mm/min)
- ⁵ 0.20 in/min (5.0 mm/min)

