

DYNAMID DYN-N66G25L NC

Polyamide 66

Dynamic Polymer Solutions

PROSPECTOR®

www.ulprospector.com

Technical Data

Product Description

Polyamide 66, 25% glass fiber reinforced & lubricated natural

General

Material Status	• Commercial: Active		
Literature ¹	• Technical Datasheet (English)		
Availability	• North America		
Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight		
Additive	• Lubricant		
Features	• Good Stiffness	• Good Strength	• Lubricated
Appearance	• Natural Color		
Processing Method	• Injection Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity			
--	1.32	1.32 g/cm ³	ASTM D792
73°F (23°C)	1.32 g/cm ³	1.32 g/cm ³	ISO 1183
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus			
-- ³	1.23E+6 psi	8490 MPa	ASTM D638
--	1.23E+6 psi	8490 MPa	ISO 527-1/10
Tensile Strength			
Yield ⁴	24100 psi	166 MPa	ASTM D638
Yield	23900 psi	165 MPa	ISO 527-2/50
Tensile Elongation			
Break ⁴	3.5 %	3.5 %	ASTM D638
Break	3.0 %	3.0 %	ISO 527-2/50
Flexural Modulus ⁵	1.10E+6 psi	7580 MPa	ASTM D790 ISO 178
Flexural Strength ⁵			
--	32500 psi	224 MPa	ASTM D790
--	37700 psi	260 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	2.7 ft·lb/in ²	5.7 kJ/m ²	ISO 179
Notched Izod Impact			
73°F (23°C)	2.0 ft·lb/in	110 J/m	ASTM D256
73°F (23°C)	5.7 ft·lb/in ²	12 kJ/m ²	ISO 180
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 psi (0.45 MPa), Unannealed	500 °F	260 °C	ASTM D648 ISO 75-2/B
264 psi (1.8 MPa), Unannealed	435 °F	224 °C	ASTM D648
264 psi (1.8 MPa), Unannealed	473 °F	245 °C	ISO 75-2/A
Peak Melting Temperature	504 °F	262 °C	ASTM D3418 ISO 3146



DYNAMID DYN-N66G25L NC

Polyamide 66

Dynamic Polymer Solutions

PROSPECTOR®

www.ulprospector.com

Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	212 to 248 °F	100 to 120 °C
Drying Time	3.0 to 5.0 hr	3.0 to 5.0 hr
Suggested Max Moisture	< 0.15 %	< 0.15 %
Processing (Melt) Temp	545 to 590 °F	285 to 310 °C
Mold Temperature	149 to 194 °F	65 to 90 °C
Injection Rate	Fast	Fast
Back Pressure	100 to 150 psi	0.689 to 1.03 MPa

Notes

¹ These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.

² Typical properties: these are not to be construed as specifications.

³ 0.39 in/min (10 mm/min)

⁴ 2.0 in/min (50 mm/min)

⁵ 0.20 in/min (5.0 mm/min)

