

DYNAMID DYN-N66G35IML NC

Polyamide 66
Dynamic Polymer Solutions

Technical Data			
Product Description			
Polyamide 66, 35% glass fiber reinforced, impact modified & lubricated natural			
General			
Material Status	• Commercial: Active		
Literature ¹	• Technical Datasheet (English)		
Availability	• North America		
Filler / Reinforcement	• Glass Fiber, 35% Filler by Weight		
Additive	• Impact Modifier	• Lubricant	
Features	• Abrasion Resistant • Chemical Resistant • Good Processability	• Good Stiffness • Good Strength • High Impact Resistance	• Impact Modified • Low Temperature Impact Resistance • Lubricated
Appearance	• Natural Color		
Processing Method	• Injection Molding		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity			
--	1.35	1.35 g/cm³	ASTM D792
73°F (23°C)	1.35 g/cm³	1.35 g/cm³	ISO 1183
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus			
-- ³	1.28E+6 psi	8800 MPa	ASTM D638
--	1.28E+6 psi	8800 MPa	ISO 527-1/10
Tensile Strength			
Yield ⁴	21200 psi	146 MPa	ASTM D638
Yield	21000 psi	145 MPa	ISO 527-2/50
Tensile Elongation			
Break ⁴	6.0 %	6.0 %	ASTM D638
Break	4.0 %	4.0 %	ISO 527-2/50
Flexural Modulus ⁵			
--	1.10E+6 psi	7580 MPa	ASTM D790
--	1.09E+6 psi	7500 MPa	ISO 178
Flexural Strength ⁵			
--	31000 psi	214 MPa	ASTM D790
--	29700 psi	205 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	4.5 ft·lb/in²	9.5 kJ/m²	ISO 179
Notched Izod Impact			
73°F (23°C)	4.0 ft·lb/in	210 J/m	ASTM D256
73°F (23°C)	11 ft·lb/in²	24 kJ/m²	ISO 180

DYNAMID DYN-N66G35IML NC

Polyamide 66

Dynamic Polymer Solutions

PROSPECTOR®

www.ulprospector.com

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 psi (0.45 MPa), Unannealed	500 °F	260 °C	ASTM D648
66 psi (0.45 MPa), Unannealed	502 °F	261 °C	ISO 75-2/B
264 psi (1.8 MPa), Unannealed	469 °F	243 °C	ASTM D648
264 psi (1.8 MPa), Unannealed	475 °F	246 °C	ISO 75-2/A
Peak Melting Temperature	504 °F	262 °C	ASTM D3418 ISO 3146

Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	212 to 248 °F	100 to 120 °C
Drying Time	3.0 to 5.0 hr	3.0 to 5.0 hr
Suggested Max Moisture	< 0.15 %	< 0.15 %
Processing (Melt) Temp	536 to 572 °F	280 to 300 °C
Mold Temperature	140 to 185 °F	60 to 85 °C
Injection Rate	Fast	Fast
Back Pressure	100 to 150 psi	0.689 to 1.03 MPa

Notes

¹ These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.

² Typical properties: these are not to be construed as specifications.

³ 0.39 in/min (10 mm/min)

⁴ 2.0 in/min (50 mm/min)

⁵ 0.20 in/min (5.0 mm/min)

